



Flexipol MBS-35

Blocked Isocyanate Cross-linking Agent

Overview

- Aqueous, blocked isocyanate (BI) cross-linking agent
- Designed to un-block/cross-link at specific temperatures/times
- Improves the wash and dry-clean fastness of DWR and Soil Release finishes
- Formaldehyde-free
- Does not discolor or stiffen hand of finished textiles

Applications

- Extending and improving durability of DWR and soil release finishes for textiles and leather
- Coatings for improved resistance to chemical and environmental attack
- Cross-linkable dispersions in aqueous pad applications for improved durability of coatings and adhesives
- Coatings with enhanced lamination adhesion
- Woven and nonwoven fabrics finished for improved resistance to blood and saline penetration
- Coatings which require a heat-curing cycle

Technical Information

Flexipol MBS-35 is a blocked isocyanate (BI) product that can be used as a latent cross-linking agent and/or adhesion promoter in industrial coating applications designed to unblock at specific curing temperatures to react fully with other functional co-binders in coating formulations.

Flexipol MBS-35 performs well in coatings which require a heat-curing cycle, including applications such as electrostatic spraying, curtain and coil coating, electrodeposition, and other manufacturing techniques.

Formulary

Mix Flexipol MBS-35 before use.

In Textile pad/dry/cure applications for soil release or durable water repellency (DWR) finishing, the typical use level of Flexipol MBS-35 is at approximately 20% of the soil release or DWR agent pad-bath charge, or 10-20% of the pad solution.

To achieve full cross-linking activity, dry/cure at 130-180°C for 3-4 minutes total dwell time. Catalyst may be needed. Pre-trial optimization is recommended.

Typical Properties

PROPERTY	VALUE
Appearance	Translucent to opaque, colorless to tan emulsion
Odor	Mild
Ionic character	Nonionic
Water solubility	Dispersible
Viscosity @25°C (Brookfield), MPa·s/cps	<1000
Total solids, %	36.0±2.0
pH (as is)	6.5±1.0
Density@25°C, g/ml	1.12±0.05
Boiling Point	100°C
Flash point	None (aqueous)
Storage	Store at 5-25°C, protect from heat* . Mix Before Use. Freeze/Thaw stable.
Shelf life	12 months

Packaging and Handling

Flexipol MBS-35 is available in:
275 gallon totes (Net Wt. 2400 lbs)
55 gallon plastic drums (Net Wt. 480 lbs)
5 gallon plastic pails (Net Wt. 40 lbs.)

*This product is sensitive to heat.

Storage at higher than recommended temperature will result in increase of color and viscosity. Prolonged or high heat exposure may cause product degradation and off-gassing that could lead to container rupture. Refer to the Safety Data Sheet (SDS) for additional information.

Whether you're looking for a replacement product or an ingredient for a specific attribute, give us a call. We can provide assistance based upon your particular formulation requirements and composition; please feel free to contact us.

Please refer to back page for important information

Flexipol MBS-35


Blocked Isocyanate (BI) cross-linking agent

Blocked isocyanate (BI) products have been used in the coating industry as cross-linking agents and adhesion promoters for decades, known for their high reactivity and selectivity towards various functional polymers, and substrates.

Functionality

Blocked isocyanate (BI) compounds are inert and nonhazardous materials that can be compounded into stable products, stored, transported, and applied to a substrate, or added to a pad application bath mix containing a soil release or DWR finishing agent.

When the coating or finish containing the BI is dried, then cured at unblocking temperatures/times sufficient to liberate free isocyanate groups, the transient free isocyanate groups react with hydroxyl or other functional groups on the co-binder polymer and/or substrate, leading to rapid cross-linking of the coating with increased covalent bonding with the substrate.



The freed blocking agent is either liberated as VOC, or remains mainly trapped in the coating.

This information relates only to the specific material referred to herein and not to its use in combination with any other material or in any process, unless explicitly stated herein. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled; however, no warranty, guarantee or other representation is made as to its accuracy, reliability, or completeness, or regarding any liabilities arising from others' intellectual property rights. ID# 20180509